



Brussels Block[®]

1-800-UNILOCK | UNILOCK.COM

UNILOCK
PAVERS & WALLS

BRUSSELS BLOCK®

CLASSIC



DESERT SAND



LIMESTONE



MAHOGANY



SANDSTONE



SIERRA



MIDNIGHT CHARCOAL

Midnight Charcoal only available in XL, Standard and Fullnose.

PRODUCT ATTRIBUTES

Visual Appearance	Original tumbled paver. Timeless warmth, relaxed appearance.
Finish	Tumbled and weathered finish.

PRODUCT SPECIFICATIONS



XL STONE
8½ x 13½ x 2¾"
208 x 348 x 70mm



STANDARD STONE
6½ x 8½ x 2¾"
173 x 208 x 70mm




HALF STONE
4½ x 6½ x 2¾"
104 x 173 x 70mm




FULLNOSE COPING
5⅞ x 11¼ x 2¾"
150 x 300 x 70mm
Available in Limestone, Sandstone and Midnight Charcoal only

EDGE DETAILS




TUMBLLED EDGE

LAYING PATTERNS




BRUSSELS AF
40% XL, 40% Standard,
20% Half


UNILOCK



BRUSSELS O
33% Half Stone, 67%
Standard



BRUSSELS P
67% Standard, 33% Half



BRUSSELS W
18% Half Stone, 23%
Standard, 59% XL

RECOMMENDED SAND



Gator G2 Super Sand

- ✓ Rain safe after 15 mins
- ✓ Sets above 32° F/ 0° C
- ✓ Can be used for joints up to a max of 2"
- ✓ Dust free and haze free
- ✓ Requires only one watering
- ✓ Two colours: Beige, Slate Grey

Coverage:

Colour	Narrow Joints	Wide Joints
Beige, Slate Grey 50lb. bag	65-85 sqft	22-42 sqft

RECOMMENDED SEALER



Gator Natural Look Sealer

- ✓ Water-based
- ✓ Zero gloss finish
- ✓ Multi purpose
- ✓ Rain safe after 24 hours

Coverage:

Size	Area
3.78 L / 1 U.S. gal.	175 sqft
18.9 L. / 5.28 U.S. gal.	875 sqft

TECHNICAL INFORMATION

ASTM C936 Standard Specifications for Solid Concrete Interlocking Paving Units

Conforms to:

- C140 for Absorption 5% avg - 7% max
- Compressive Strength > 7,200 PSI avg.
- C67 for Freeze-thaw Durability
- C418 for Abrasion Durability
- Dimensional Accuracy **+/- 3mm**

Test results available upon request

Meets the U.S. Architectural & Transportation Barrier Compliance Board Slip-Resistance Surfaces Advisory Guidelines

TECHNICAL ADVANTAGES

CLASSIC

Budget-friendly. Utilize a traditional product mix of large and small aggregates that's consistent from top to bottom with colour mixed throughout

ANTIQUED FINISH

Distressed, timeworn finish

DRIVE FRIENDLY

Can handle vehicular loads

PRODUCT DATA

Stones & Bundling	Unit	SqFt Per				Per Bundle		Soldier LnFt Per			Sailor LnFt per			Units Per			Lbs Per		
	Thickness	Bundle	Layer	Section	Stone	Layers	Sections	Unit	Section	Bundle	Unit	Section	Bundle	SqFt	Section	Bundle	Layer	Section	Bundle
Ayr manufacturing																			
XL	2¾" (70mm)	95.94	11.99	31.98	0.80	8	3	1.17	27.3	81.9	0.70	45.7	137.0	1.25	40	120	378	1,008	3,024
Standard	2¾" (70mm)	95.94	11.99	19.19	0.40	8	5	0.70	27.2	136.2	0.58	32.8	163.8	2.50	48	240	383	613	3,064
Half	2¾" (70mm)	95.94	11.99	15.99	0.20	8	6	0.59	27.3	163.8	0.35	-	272.4	5.00	80	480	372	496	2,976

Notes: All measurements are nominal. Contact your Unilock Territory Manager or call 1-800-UNILOCK for further information. *For custom options, please contact your Unilock Territory Manager.

APPLICATIONS



Pedestrian



Residential Vehicular



Borders and Accents



Wall pairing suggestion- Brussels Dimensional Stone - matching colour and finish

SOLAR REFLECTIVE INDEX (SRI) TESTING DETAILS

Product	Solar Reflectance	SRI
Limestone	0.28	29
Sandstone	0.41	46

LEED INFORMATION

Materials & Resources: LEED V4:

Building Product Disclosure and Optimization

Sourcing of Raw Materials - Sourcing of Raw Materials and Extraction • **1 point**

Sourcing of Raw Materials - Leadership Extraction Practices • **1 point**

Material Ingredient Reporting - Material Ingredient Reporting • **1 point**

Material Ingredient Reporting - Material Ingredient Optimization • **1 point**

Environmental Product Declaration • **1 point**