



# Treo<sup>®</sup> Smooth

1-800-UNILOCK | [UNILOCK.COM](http://UNILOCK.COM)

**UNILOCK**  
PAVERS & WALLS

# TREO<sup>®</sup> SMOOTH

CLASSIC  PERMEABLE

**NEW FOR 2021**



GRANITE BLEND

## PRODUCT ATTRIBUTES

Visual Appearance	Treo Smooth offers a smooth surface texture for a sleek, modern look with a contemporary colour palette.
Finish	Smooth, classic appearance.

## PRODUCT SPECIFICATIONS



**LARGE RECTANGLE**  
8 <sup>7</sup>/<sub>8</sub> x 13 <sup>1</sup>/<sub>2</sub> x 3 <sup>1</sup>/<sub>8</sub>"  
226 x 343 x 80mm




**SQUARE**  
8 <sup>7</sup>/<sub>8</sub> x 8 <sup>7</sup>/<sub>8</sub> x 3 <sup>1</sup>/<sub>8</sub>"  
226 x 226 x 80mm



**SMALL RECTANGLE**  
4 <sup>1</sup>/<sub>4</sub>" x 8 <sup>7</sup>/<sub>8</sub> x 3 <sup>1</sup>/<sub>8</sub>"  
110 x 226 x 80mm

3 UNIT RANDOM BUNDLE

## EDGE DETAILS



ROUNDED EDGE

## RECOMMENDED SAND



**Gator G2 MAXX Sand**

- | Setting time - 15 mins
- | Sets above 32° F/ 0° C
- | Can be applied if rain is expected (min. 1 hr)
- | Dust free and haze free
- | Requires only one watering
- | Four colours: Beige, Grey, Black and Ivory

### Coverage:

Colour	Narrow Joints	Wide Joints
Beige, Grey, Ivory <i>50lb. bag</i>	65-85 sqft	22-42 sqft
Black <i>50lb. bag</i>	58-76 sqft	20-38 sqft

## RECOMMENDED SEALER



**Gator Natural Look Sealer**

- | Water-based
- | Zero gloss finish
- | Multi purpose
- | Rain safe after 24 hours

### Coverage:

Size	Area
3.78 L / 1 U.S. gal.	175 sqft
18.9 L. / 5.28 U.S. gal.	875 sqft

## TECHNICAL INFORMATION

### ASTM C 936 Standard Specifications for Solid Concrete Interlocking Paving Units

Conforms to:

- C140 for Absorption 5% avg - 7% max
- Compressive Strength > 7,200 PSI avg.
- C67 for Freeze-thaw Durability
- C418 for Abrasion Durability
- Dimensional Accuracy **+/- 3mm**

*Test results available upon request*

**Meets the U.S. Architectural & Transportation Barrier Compliance Board Slip-Resistance Surfaces Advisory Guidelines**

## TECHNICAL ADVANTAGES

### CLASSIC

Budget-friendly. Utilize a traditional product mix of large and small aggregates that's consistent from top to bottom with colour mixed throughout



#### PERMEABLE

Can be installed to allow water to flow through

### DRIVE FRIENDLY

Can handle vehicular loads

*Ask about our base stabilization system*

## PRODUCT DATA

	Unit	SqFt Per				Per Bundle		Soldier LnFt Per			Sailor LnFt per			Units Per		Lbs Per		
Stones & Bundling	Thickness	Bundle	Layer	Section	Stone	Layers	Section	Unit	Section	Bundle	SqFt	Layer	Bundle	SqFt	Bundle	Layer	Section	Bundle
Ayr Manufacturing																		
Random Bundle		93.50	11.69			8	-	-	-	-	-		74.4	0.77	168	427.63	-	3,421
Large Rectangle	3½" (80mm)	42.07	5.259	-		8	-	-	-	-	-		24.8	0.48	48	192.45	-	1,539.64
Square	3½" (80mm)	32.72	4.091	-		8	-	-	-	-	-		24.8	0.72	56	149.69	-	1,197.50
Small Rectangle	3½" (80mm)	18.70	2.337	-		8	-	-	-	-	-		24.8	1.43	64	85.54	-	684.29

Notes: Sold in full bundles only on a refundable skid. All measurements are nominal. **Important: A urethane rubber paver mat must be used to prevent scuffing.** Contact your Unilock Territory Manager or call 1-800-UNILOCK for further information. \*For custom options, please contact your Unilock Territory Manager.

## APPLICATIONS



Pedestrian



\*Wall pairing suggestion- U-CARA\* - matching colour and finish



Residential Vehicular




Commercial Vehicular

### \*Paver Maintenance Tips:

- Equip plow scrapers and blades with shoes or high-density plastic blades to reduce the risk of damaging paver joints and the surface
- Only apply min. amount of de-icing salts necessary to melt the snow and ice. Remove excess salt after ice melts
- Regular cleaning routine should include sweeping or blowing loose debris from the pavement surface, and less frequently, deep cleaning with cleaning products and/or water
- Unilock pavers do not require sealing, however, some people choose to do so for aesthetic purposes

### \*Things to know:

Efflorescence is a naturally occurring calcium salt that can sometimes appear on the surface of concrete and clay products. Efflorescence does not affect the structural integrity of concrete, it is a purely aesthetic issue that typically disappears with no further intervention after a season of rainfall. If desired, the process can be accelerated by washing the surface with an Efflorescence Remover.

 For Permeable applications- it is recommended that the jointing material be regularly maintained, including vacuuming, cleaning and reapplying to keep infiltration at its maximum potential.